

## Specification of Premium Wood Pellets - ENplus A1

<b>Parameter</b>	<b>Value</b>	<b>Method of analysis</b>
Moisture:	Maximum 8%	CEN/TS 14774-2
Ash (measured at 550 °C):	Maximum 0,50 %	CEN/TS 14775
Sulphur:	Maximum 0,04% d.b.	Leco / SS 18 77 77
Chlorides:	Maximum 0,02%	SS 18 71 85
Net calorific value, (Constant pressure)	Min. 17,5 GJ/ton, net as received	CEN/TS 14918
Size, diameter:	6 mm	
Bulk Density:	Minimum 650 kg/m <sup>3</sup>	SS 18 71 78
Particle size:	Minimum 95% of the particles smaller than 2 mm	CEN/TS 15149-2
Fines:	Max. 5 % fines < 3,15 mm	SS 18 71 80
Durability:	min. 98 %	
Ash fusion temperature, flow	Min. 1.250 °C	