

TDS N°511

CERA D'ARTE COLOSSEO

CERA D'ARTE COLOSSEO

DESCRIPTION

CERA D'ARTE COLOSSEO is a natural bee's wax polish, protective and decorative. The product comes in two versions: the classic wax polish and the decorative version in gold and silver. CERA D'ARTE COLOSSEO is applied on decorative plasters, glazes and paints. Wax does not yellow long after a long time after being applied

APPLICATION

Mix well before using.

Apply the wax with a stainless steel trowel or cloth. After complete drying polish the wax with cotton or polishing machine.

If the product is liquid before the application you refrigerate for dense

Apply a very thin layer of CERA D'ARTE COLOSSEO using short (small) spatulas starting from the bottom and continuing upwards to avoid stains due to excessive absorption of the support

TECHNICAL DATA	
Nature of the bond	Bees wax in special resins
Viscosity	
Drying Time	2 h at touch, 6-12 h complete.
Thinning	Ready to use
Yield	20-33m²/Lt
Specific weight	0,750Kg/Lt
Colors	Neutral, gold, silver
Dry aspect	Transparent or iridescent
Wet aspect	Neutral transparent or iridescent
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 Years (in sealed, unopened original packing)
VOC	N/AμGr/m³
TVOC	N/AμGr/m³
РН	7-8°C
Cleaning	Water
Packing	0.750LT
CHARACTERISTICS	
Characteristics:	
Can be applied on:	Walls.
for:	Interiors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Spalter, Cloth.
Related products:	N/A.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions. The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge, however, being elements such as weather conditions, labor, tools, quality of third party products and others, not under the direct control of the Rivedil, this document does not constitute a warranty, nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document. We recommend that you always check the suitability of the product to each specific instance. This supersedes all previous editions.