HOLTTEM AS LOG QUALITY REQUIREMENTS

2 February 2023

1. The *seller* sells and the *buyer* purchases felled *timber*, the quality and dimensions of which are stipulated below:

	hases felled timber, the quality and dimens		
Diameter at the top end, stripped of bark:		Min 16 cm	
Maximum diameter of the lower end, with bark:		Max 60 cm	
Lengths:	36–51 dm, in increments of 3 dm		
Auxiliary measure:	None		
Overlength	Min 7 cm		
Fault name / Quality	ABC	D	
Sound knot	Permitted Ø for spruce <70 mm, pine	Ø for spruce <80 mm, pine <100	
	<80 mm, quantity unlimited	mm, quantity unlimited	
Dry knot	Permitted Ø for spruce <60 mm, pine	Ø for spruce <70 mm, pine <90	
	<70 mm, quantity unlimited	mm, quantity unlimited	
Unsound knot	Permitted Ø for spruce <40 mm, pine	Ø for spruce <50 mm, pine <80	
	<60 mm, quantity unlimited	mm, quantity unlimited	
Intergrown knots	Permitted		
Splay knots	Forbidden	Permitted	
Cluster knots	Forbidden	Permitted	
Branch stub (bad) height	Permitted <30 mm	Permitted <50 mm	
Simple sweep	Permitted evenly over the entire		
	length of the log: on a log with a	nitted evenly over the entire length	
Simple sweep	length of 30 dm <1.3%, on longer	of the log: <2%	
	logs <1.5%		
Multiple sweep	Forbidden in the processing cylinder	Forbidden in the processing	
		cylinder	
Sharp sweep	Forbidden		
Butt-end area cracks	Forbidden traversing cracks in butt-	Permitted traversing cracks in butt-end areas at a distance of	
	end areas and circular cracks		
		<200 mm	
Edge cracks	Forbidden in the effective length and in the processing cylinder		
	Permitted up to the two-fold length	Permitted	
Outer inbark	of the higher end diameter on one		
	side of the log outside the processing		
T . 1 1	cylinder	B	
Inner inbark	Forbidden in the processing cylinder	Permitted	
Soft rot	Forbidden		
Hard rot	Forbidden		
Sap rot	Forbidden		
Stockiness	Forbidden	Forbidden	
Double pith	Forbidden	Permitted	
Log blue	Forbidden	Permitted	
Grub holes	Permitted surface fault	Permitted	
Resin tapping (including double-	Forbidden	Permitted	
sided)			
Mechanical damage (including	Permitted <7 mm under bark	Permitted without limitation in the	
damage by harvester rollers)		processing cylinder at length of	

		<600 mm; Permitted damage by
		harvester rollers <20% of the
		diameter of the processing
		cylinder along the entire length of
		the log
Metal content, soot, foreign bodies	Forbidden	Forbidden
Dead-and-down	Forbidden	Forbidden

Holttem AS
(signed digitally)
Mikk Kullamaa
Member of the management board